

Data sheet article FE-Q-50-50-05

Technical data and application safety

Webcraft GmbH Industriepark 206 78244 Gottmadingen, Germany Phone: +49 7731 939 839 1

www.supermagnete.nl support@supermagnete.nl

1. Technical information

Block magnet 50 x 50 x 5 mm, holds approx. 2 kg, ferrite, Y35, no coating

Article ID	FE-Q-50-50-05
EAN	7640155431897
Material	Ferrite
Shape	Block
Size	50 x 50 x 5 mm
Side 1	50 mm(+/- 1,0 mm)
Side 2	50 mm(+/- 1,0 mm)
Side 3	5 mm(+/- 0,1 mm)
Pole faces	50 x 50 mm
Direction of magnetisation	5 mm
Coating	No coating
Manufacturing method	sintered
Magnetisation	Y35
Strength	approx. 2 kg (approx. 19,6 N)
Displacement force	approx. 390 g (approx. 3,82 N)
Max. working temperature	250°C
Colour	Grey
Weight	60,6250 g
Curie temperature	450 °C
Residual magnetism Br	4000-4100 G, 0.40-0.41 T
Coercive field strength bHc	2.20-2.45 kOe, 175-195 kA/m
Coercive field strength iHc	
Energy product (BxH)max	3.8-4.0 MGOe, 30.0-32.0 kJ/m ³


Product compliant with the latest European REACH regulation.

Product compliant with the latest European RoHS directive.

2. Safety tips

RoHS)

REACH



3. Handling and storing

Caution	Magnetic field
Λ	Magnets produce a far-reaching, strong magnetic field. They could damage TVs and laptops, computer hard drives, credit and ATM cards, data storage media, mechanical watches, hearing aids and speakers.
	 Keep magnets away from devices and objects that could be damaged by strong magnetic fields. Please refer to our table of recommended distances: www.supermagnete.nl/eng/faq/distance
Notice	Influence on people
	According to the current level of knowledge, magnetic fields of permanent magnets do not have a measurable positive or negative influence on people. It is unlikely that permanent magnets constitute a health risk, but it cannot be ruled out entirely.
6	 For your own safety, avoid constant contact with magnets. Store large magnets at least one metre away from your body.
Notice	Temperature resistance
	Ferrite magnets can be used at temperatures between -40°C and 250°C. At lower and higher temperatures they lose part of their adhesive force permanently.
	Don't use ferrite magnets in places where they are exposed to temperatures below -40°C or above 250°C.
Notice	Mechanical treatment
	Ferrite magnets are brittle. When drilling or sawing a magnet with improper tools, the magnet may break.
	Stay away from mechanical treatment of magnets if you do not possess the necessary equipment and experience.

4. Transportation tips

Caution	Airfreight		
	Magnetic fields of improperly packaged magnets could influence airplane navigation devices. In the worst case it could lead to an accident.		
	 Airfreight magnets only in packaging with sufficient magnetic shielding. Please refer to the respective regulations: www.supermagnete.nl/eng/faq/airfreight 		
	Postage		
Caution	Postage		
Caution	Postage Magnetic fields of improperly packaged magnets could cause disturbances in sorting machines and damage fragile goods in other packages.		

TARIC-Code: 8505 1910 90 0

Origin: China

For more information about magnets please review **https://www.supermagnete.nl/eng/faqs**.

Last update: 17/05/2025